

TEST REPORT

REPORT NUMBER : TURR130093425
APPLICANT NAME : Kervan Tekstil Plastik Ambalaj San.Tic.Ltd.Şti.
ADDRESS : Hacıyüplü Mah. 3215 Sok. No: 3 DenizliGümüşler Denizli / TÜRKİYE
TEL:0258 3720542FAX:0258 3721912
Attention : Murat Balta (info@kervantekstil.com)
SAMPLE DESCRIPTION : One sample of Transparent PVC film
DATE IN : 19 June ,2013 (11:33)
DATE OUT : 24 June ,2013

	SAMPLE
TEST	1
Phthalate Content	P


P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE / LS = LACK OF SAMPLE / NC = NO COMMENT / I = INCONCLUSIVE

The test results relate only to the items tested. The whole and/or the part of this test report shall not be reproduced and shall not be shared with third parties, nor to be used for PR activities without the written permission of INTERTEK Test Hizmetleri A.S.

The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and UKAS accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation. Tests marked (*) in this test report are not included in the UKAS accreditation schedule for this laboratory.



Bora Şirinbilek
COORDINATOR



Neslihan Sözer
Chemical Laboratory Manager



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altındağ Plaza Yenibosna-34197 /ISTANBUL

Phone : +90 212 496 46 46 Fax: +90 212 452 80 55

e-mail : intertekcg.turkiye@intertek.com

<http://www.intertek-turkey.com>

130093425

Test Method	Results	Requirements
-------------	---------	--------------

Phthalate Content

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

Method By Gas Chromotography- Mass Spectrometry (GC- MS) Analysis

	RESULT (% , w/w)
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
DI-N-PENTYL PHTHALATE (DnPP)	ND
SUM OF ALL PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Limit of 0.1% by weight was quoted according to Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content

ppm (part per million) =mg / kg < =Less Than * =EXCEEDED LIMIT ND = NOT DETECTED
 Detection Limit = DINP,DIDP : 100 ppm, Other Phthalates : 10 ppm

Estimated Total Uncertainty=(±5%)





END OF TEST REPORT